

TECHNICAL DATA SHEET

ARTICLE: CLASSIC-BASE-GLASS
ITEM-NO.: JB1823-0-001
SYSTEM: Solvent-Based, 1C Primer



PRODUCT PROPERTIES

CLASSIC-BASE-GLASS JB1823-0-001 is a transparent, solvent-based, 1C primer and is characterised by:

- easy-to-use
- extra fast drying

SCOPE OF APPLICATION

Suitable for coating of:

- glass

TECHNICAL DATA

APPLICATION

■ Colour: transparent

■ Gloss level: -

■ Viscosity: 9-11 s DIN 53211/ 4 mm

■ Density: approx. 0,7875 g/cm³



Application quantity per layer (g/m²)

30-50

Quantity of applied layers

1

Jet nozzle (mm)

1,2-1,5

Air pressure (bar)

2,0-3,0

Material pressure (bar)

DRYING

HARDENER, THINNER, RETARDER

Dust-dry after 10 min

Sandable after


Overcoatable after 10-20 h

Stackable after

Completely dried after

Cured after

(at 20 °C and 35-65 % relative humidity and depending on the applied quantity)



Hardener

-

Thinner

-

Retarder

-

Item No.: JB1823-0-001

STORAGE



Store material in a tightly closed container and under dry and cool conditions. Protect from frost.

Shelf life:

JB1823-0-001: 6 months

(when stored in the original unopened containers)

CLEANING



Clean tools immediately after use with

- Nitro-Thinner JT1415-0-001 or
- DD-Thinner JT1244-0-001 or
- UNI-CLEAN JT1803-0-001

SPECIAL GUIDANCE

- Stir well before using!
- The substrates which should be coated have to be conditioned 12 hours before coating.
- It is recommended to perform preliminary trials to test the suitability of the coating system with the desired substrate.
- The surfaces have to be perfectly sanded, dry, free of grease, oil and silicones before the application.
- High humidity and a moisture content above 10% must be avoided at all costs. High humidity leads to longer drying times. The indicated times depend on the application quantity, the room temperature and the relative humidity.
- Protect the containers from drying out and always close them tightly immediately after removing the material.
- Solvent-based products are flammable, also during processing and drying.
- If too much 1K CLASSIC-BASE-GLASS JB1823-0-001 is applied, this may result in whitish stains and streaks which will spoil the subsequent finish.
- The surfaces can be painted over with JORA-COLOR JK2150 and HIGH-SOLID-COLOR JK2600.

TESTING STANDARDS

Safety guidance:

The information in this technical data sheet is based on the current knowledge and experience of PLANTAG Coatings GmbH. The product processor is not exempted from its own testing and testing of the products with regard to the intended use as well as the wealth of possible influences during processing and application. Existing laws and regulations are to be observed by the recipient of our products in their own responsibility. Labeling in accordance with the Ordinance on Hazardous Substances and Transport Law can be found in the safety data sheet. A legally binding assurance of certain properties or suitability for a specific purpose cannot be derived from our information. Recommendations deviating from the information in our technical data sheets are only binding for us if they have been confirmed in writing. Our terms and conditions are an integral part of this technical information sheet [Jul-25]

PLANTAG Coatings GmbH

Ohmstr. 8
32758 Detmold
GERMANY
Fon: +49 5231 6002 661
Fax: +49 5231 6002 9661
E-Mail: info@jordanlacke.de

JORDAN LACKE – a brand of PLANTAG Coatings GmbH