


**ARTICLE:** CLASSIC-EXTREME-RESIST  
**ITEM-NO.:** JM2894  
**SYSTEM:** Solvent-Based, 2C Top Coat



## PRODUCT PROPERTIES

CLASSIC-EXTREME-RESIST JM2894 is a transparent, solvent-based, 2C top coat and is characterised by:

- extremely high mechanical resistance
- anti-fingerprint effect
- fast drying
- easy-to-use

## SCOPE OF APPLICATION

Suitable for coating of:

- several solid timbers (Except tropical and ingredient rich woods)
- veneered substrates

The product is well suited for the application on:

- furniture surfaces
- surfaces in kitchen and bathroom areas

## TECHNICAL DATA

- Colour: transparent
- Gloss level: JM2894-2-001 deep matt  
JM2894-1-001 naturmatt
- Viscosity: 29-32 s DIN 53211/ 4 mm
- Density: approx. 0,933 g/cm<sup>3</sup>




## APPLICATION



Application quantity per layer (g/m <sup>2</sup> )	120-160	
Quantity of applied layers	1-2	
Jet nozzle (mm)	1,5-2,0	0,28-0,33
Air pressure (bar)	2,0-3,0	1,0-1,5
Material pressure (bar)		100-120

## DRYING

## HARDENER, THINNER, RETARDER

Dust-dry after	30 min		Hardener	10:1 by volume with hardener JH2132-0-001	
Sandable after	2-3 h			Pot life	with hardener JH2132-0-001: 24 h (shortens at high temperatures)
Overcoatable after				Thinner	If necessary: JT1244-0-001 add max.: 10 %
Stackable after	24 h			Retarder	If necessary: JT1019-0-001 add max.: 5 %
Completely dried after	24 h				
Cured after	7-10 d				
( at 20 °C and 35-65 % relative humidity and depending on the applied quantity)					

Item No.: JM2894

## STORAGE



Store material in a tightly closed container and under dry and cool conditions. Protect from frost.

### Shelf life:

JM2894: 6 months

Hardener JH2132-0-001: 6 months

(when stored in the original unopened containers)

## CLEANING



Clean tools immediately after use with

- Nitro-Thinner JT1415-0-001 or
- DD-Thinner JT1244-0-001 or
- UNI-CLEAN JT1803-0-001

## SPECIAL GUIDANCE

- Stir well before using!
- Hardener and lacquer must be thoroughly mixed!
- The substrates which should be coated have to be conditioned 12 hours before coating.
- It is recommended to perform preliminary trials to test the suitability of the coating system with the desired substrate.
- The surfaces have to be perfectly sanded, dry, free of grease, oil and silicones before the application.
- High humidity and a moisture content above 10% must be avoided at all costs. High humidity leads to longer drying times. The indicated times depend on the application quantity, the room temperature and the relative humidity.
- Protect the containers from drying out and always close them tightly immediately after removing the material.
- Solvent-based products are flammable, also during processing and drying.
- Thoroughly mix the hardener and the lacquer!
- Not suitable for coating resin-rich wood species, as well as unsealed wood core panels and rotary cut veneer panels.
- It can be used to coat coloured lacquer JORA-COLOR JK2150 and base coats JB2450-0-001, JB2010-0-001 and JM2310-0-001.
- GIESS-COLORLUX JM2370 can be used as a base coat for open-porous coatings.

## TESTING STANDARDS

- EN 71, part 3 free of extractable heavy metals
- DIN 53160 resistant to saliva and perspiration
- DIN-68861-1B chemical resistance
- PVC - resistant
- Formaldehyde-free

### Safety guidance:

The information in this technical data sheet is based on the current knowledge and experience of PLANTAG Coatings GmbH. The product processor is not exempted from its own testing and testing of the products with regard to the intended use as well as the wealth of possible influences during processing and application. Existing laws and regulations are to be observed by the recipient of our products in their own responsibility. Labeling in accordance with the Ordinance on Hazardous Substances and Transport Law can be found in the safety data sheet. A legally binding assurance of certain properties or suitability for a specific purpose cannot be derived from our information. Recommendations deviating from the information in our technical data sheets are only binding for us if they have been confirmed in writing. Our terms and conditions are an integral part of this technical information sheet [Jul-25]

### PLANTAG Coatings GmbH

Ohmstr. 8  
32758 Detmold  
GERMANY  
Fon: +49 5231 6002 661  
Fax: +49 5231 6002 9661  
E-Mail: info@jordanlacke.de

JORDAN LACKE – a brand of PLANTAG Coatings GmbH