

**Basic Shades**




JC1731-00001  
white



JC1731-01001  
yellow



JC1731-03001  
red



JC1731-05001  
blue



JC1731-06001  
green



JC1731-09001  
black



Card shade 732-20  
80 P yellow, 12 P red, 8 P black, 50% JC1927-0-001



Card shade 732-21  
90 P yellow, 8 P red, 2 P black, 50% JC1927-0-001



Card shade 732-22  
34 P yellow, 33 P red, 33 P green, 50% JC1927-0-001



Card shade 832-20  
80 P yellow, 12 P red, 8 P black, 50% JC1928-0-001



Card shade 832-21  
90 P yellow, 8 P red, 2 P black, 50% JC1928-0-001



Card shade 832-22  
34 P yellow, 33 P red, 33 P green, 50% JC1928-0-001



Card shade 732-23  
88 P yellow, 5 P red, 5 P black, 2 P green,  
50% JC1927-0-001



Card shade 732-24  
55 P yellow, 15 P red, 10 P black, 20 P green,  
50% JC1927-0-001



Card shade 732-25  
75 P yellow, 10 P red, 12 P black, 3 P blue,  
50% JC1927-0-001

**Card shade**



Card shade 832-23  
88 P yellow, 5 P red, 5 P black, 2 P green,  
50% JC1928-0-001



Card shade 832-24  
55 P yellow, 15 P red, 10 P black, 20 P green,  
50% JC1928-0-001



Card shade 832-25  
75 P yellow, 10 P red, 12 P black, 3 P blue,  
50% JC1928-0-001



Card shade 732-26  
20 P yellow, 40 P red, 20 P black, 20 P blue,  
50% JC1927-0-001



Card shade 732-27  
25 P yellow, 45 P red, 30 P blue,  
50% JC1927-0-001



Card shade 732-28  
40 P red, 40 P black, 20 P green,  
50% JC1927-0-001



Card shade 832-26  
20 P yellow, 40 P red, 20 P black, 20 P blue,  
50% JC1928-0-001




Card shade 832-27  
25 P yellow, 45 P red, 30 P blue,  
50% JC1928-0-001



Card shade 832-28  
40 P red, 40 P black, 20 P green,  
50% JC1928-0-001



Card shade 732-29  
50 P yellow, 50 P red, 50% JC1927-0-001



Card shade 732-30  
35 P yellow, 60 P red, 5 P blue, 50% JC1927-0-001



Card shade 732-31  
28 P yellow, 50 P red, 8 P black, 14 P blue,  
50% JC1927-0-001

# CLASSICSTAIN SOLVENT-STAIN

## JC1731 - JC1833

Solvent-based stains consisting of a mixture of micronised pigments and dyes, for spraying and wiping/spreading.

By adding brightener CLASSICSTAIN-STANDARD JC1927-0-001 for wiping and spreading, a pore-emphasised stain pattern (rustic effect) can be achieved on wood types such as oak, ash, walnut and mahogany.

In addition to coarse-pored woods, CLASSICSTAIN JC1832 can be used as a quick-drying spray stain on fine-pored wood types such as beech and maple after adding brightener CLASSICSTAIN-RAPID JC1928-0-001.

The sprayable version of CLASSICSTAIN JC1832 stain is ideal for patination work and for colouring our solvent-based clear coats.

### Notes:

- With the exception of white (JC1731-00001), the base colours JC1731-01001 to JC1731-09001 must only be used in diluted form!
- The effect of the stain depends on many factors, including the type of wood, the condition of the wood, the wood grinding, the application method, the amount applied, the exposure time of the stain and the lacquer coating. It is therefore essential that, before starting the staining work, a sample is produced on the wood or veneer to be used, followed by lacquering.
- The stain colours shown in the stain chart are for guidance only. They are not binding in terms of the original delivery (subject to minor colour variations).
- To protect bright stain colours, add 1% CLASSIC-PRO-UV-PROTECT JA9045-0-001 light protection concentrate to the lacquers.

Please refer to the product data sheet for technical processing instructions. The data sheet is always available in its latest version on our website at [www.jordanlacke.de](http://www.jordanlacke.de).



### PLANTAG Coatings GmbH

Ohmstraße 8  
32758 Detmold  
GERMANY

Fon +49 5231 6002 661  
E-Mail [info@jordanlacke.de](mailto:info@jordanlacke.de)

**JORDAN Lacke – a brand of PLANTAG Coatings GmbH**

**SHOW WHAT YOU  
ARE ABLE TO DO!  
[WWW.JORDANLACKE.DE](http://WWW.JORDANLACKE.DE)**